

	PET	PA	PP	PE		PET	PA	PP	PE
MINERAL ACIDS					SALTS				
Hydrochloric Acid	G	B	G	G	Sodium Acetate	G	G	G	G
Chromic Acid	G	L	G	G	Sodium Benzoate	G	G	G	G
Hydrofluoric Acid	L	B	G	G	Sodium Bisulphate	L	G	G	G
Phosphoric Acid	G	B	G	G	Sodium Bromide	G	G	G	G
Nitric Acid	L	B	G	G	Sodium Cyanide	G	G	G	G
Sulphuric Acid	B	B	L	L	Aluminium Chloride	B	L	G	G
Aqua Regia	L	B	B	L	Ammonium Chloride	B	L	G	G
ORGANIC ACIDS					Barium Chloride	G	G	G	G
Acetic Acid	G	B	G	G	Calcium Chloride	G	G	G	G
Benzoic Acid	G	L	G	G	Ferric Chloride	G	G	G	G
Butyric Acid	G	G	G	G	Magnesium Chloride	G	G	G	G
Formic Acid	G	B	G	G	Sodium Chloride	G	G	G	G
Phtalic Acid	G	L	G	G	Zinc Chloride	G	G	G	G
Lactic Acid	G	B	G	G	Sodium Nitrate	G	L	G	G
Oleic Acid	G	G	L	L	Aluminium Sulphate	G	G	G	G
Oxalic Acid	G	B	L	G	Copper Sulphate	G	G	G	G
Salicylic Acid	L	G	G		Sodium Sulphate	G	G	G	G
BASES					Sodium Sulphide	G	G	G	G
Calcium Carbonate	G	G	G	G					
Potassium Carbonate	G	G	G	G					
Sodium Carbonate	L	G	G	G					
Ammonium Hydroxide	G	G	G	G					
Calcium Hydroxide	G	G	G	G					
Potassium Hydroxide	B	L	G	G					
Sodium Hydroxide	B	L	G	G					

Top Zeven b.v.

Wateringweg 34, 2031 EJ Haarlem, Netherlands,
tel +31(0)23 5319051, fax +31(0)23 5319065
filter@topzeven.com , www.topzeven.com

PET = Polyester

PA = Polyamide

PP = Polypropylene

PE = Polyethylene

G = Good

B = Bad

L = Limited