

Chemical Resistance to Agents

	PET	PA	PP	PE		PET	PA	PP	PE
OXIDISING AGENTS					ORGANIC SOLVENTS				
Peracetic Acid	L	L	G	B	Chloroform	G	B	B	B
Potassium Bichromate	G	L	G	L	Ethyl Chloride	G	G	L	L
Bromine	L	B	B	L	Ether Benzene	G	G	B	B
Sodium Chlorite	B	B	G	G	Ethyl Ether	G	G	L	L
Potassium Chloride	L	L	G	G	Diethylene Glycol	L	G	G	G
Chlorine	L	B	B	B	Ethylene Glycol	L	G	G	G
Fluorine	L	B	B	L	Propylene Glycol	B	G	G	L
Sodium Hypochlorite	L	L	L	L	Methyl Ethyl Acetone	G	G	L	L
Ozone	G	B	L	L	Carbon Tetrachloride	G	G	B	B
Potassium Permanganate	G	B	G	B	Toluene	G	G	L	L
Hydrogen Peroxide	G	B	L	B	Trichloroethylene	G	L	L	L
Iodine Solution	L	B	G	B	Xylene	G	G	B	B
Calcium Hypochlorite	G	L	G	G	MISCELLANEOUS				
ORGANIC SOLVENTS					Aceldahide (in water)	L	L	L	G
Amyl Acetate	G	L	G	L	Aniline	G	G	L	L
Butyl Acetate	G	G	L	L	Benzaldehyde (in water)	G	L	L	L
Ethyl Actetate	G	G	L	L	Cresol	L	B	B	L
Acetone	G	G	G	G	Phenol	B	B	L	L
Amyl Alcohol	G	G	G	G	Formaldehyde	G	G	G	G
Ethyl Alcohol	G	G	G	G	Glycerine	G	G	G	G
Methyl Alcohol	G	G	G	G	Naphta	G	G	L	L
Benzene	G	G	L	L	Nitrobenzol	L	L	G	G
Carbon Bisulfide	L	G	B	G	Mineral oil	G	G	L	G
Cyclohexanone	G	G	L	B	Tricresyl Phosphate	G	G	B	L

Top Zeven b.v.

Wateringweg 34, 2031 EJ Haarlem, Netherlands,
tel +31(0)23 5319051, fax +31(0)23 5319065
filter@topzeven.com , www.topzeven.com

PET = Polyester

PA = Polyamide

PP = Polypropylene

PE = Polyethylene

G = Good

B = Bad

L = Limited